

## Industrial matting SBR NR - A 9506 | D70

SBR-NR, black, commercial
Sulphur crosslinked
Matting with hammerblow surface (one side hammerblow dessin/one side cloth impression Height of hammerblow dessin ~ 0,7 mm
*SVHC-free

Hardness [Shore A]:	ISO 7619-1	70 ±7
Density [g/cm <sup>3</sup> ]:	ISO 1183-1	~1,46
Tensile strength [N/mm <sup>2</sup> ]:	ISO 37 type 2	4
Elongation at break [%]:	ISO 37 type 2	200
correspond to WDK-guideline 2201 : 2020-10 "Quality characteristics of Elastomer sheets and plates"		
Ozone resistance:	non resistant	
Weather resistance:	non resistant	
Oil resistance:	non resistant	
Fuel resistance:	non resistant	
Acid resistance:	moderately resistant	
Strong bases:	moderately resistant	
Abrasion resistance:	non suitable	

### WORKING TEMPERATURE RANGE

Medium	dyn. (stat.)	max.	short-term
Air	-10 (-30) °C	+70 °C	+90 °C

### COMPRESSION SET DIN ISO 815

Duration	Temperature	CS
22 h	+70 °C	50 %

### ROTA-CURED SHEETS

Article nr.	Thickness mm	Width m	Length m
4024 99050	3.0	1.4	10
4024 99035	3.0	1.25	10
4024 99054	5.0	1.4	10
4024 99070	5.0	1.25	10

